

Book Chapter

Fluorescent Single-Walled Carbon Nanotubes for Protein Detection

Adi Hendler-Neumark and Gili Bisker*

Department of Biomedical Engineering, Faculty of Engineering, Tel-Aviv University, Israel

***Corresponding Author:** Gili Bisker, Department of Biomedical Engineering, Faculty of Engineering, Tel-Aviv University, Tel Aviv 6997801, Israel

Published **December 02, 2021**

This Book Chapter is a republication of an article published by Adi Hendler-Neumark and Gili Bisker at Sensors in December 2019. (Hendler-Neumark, A.; Bisker, G. Fluorescent Single-Walled Carbon Nanotubes for Protein Detection. Sensors 2019, 19, 5403. <https://doi.org/10.3390/s19245403>)

How to cite this book chapter: Adi Hendler-Neumark, Gili Bisker. Fluorescent Single-Walled Carbon Nanotubes for Protein Detection. In: Yuwen Li, editor. Prime Archives in Sensors: 2nd Edition. Hyderabad, India: Vide Leaf. 2021.

© The Author(s) 2021. This article is distributed under the terms of the Creative Commons Attribution 4.0 International License (<http://creativecommons.org/licenses/by/4.0/>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Funding: This research was supported by the Zuckerman STEM Leadership Program (G.B.) the Israel Science Foundation (grant No. 456/18), The Ministry of Science, Technology, and Space, Israel (grant No. 3-17426), the Nicholas and Elizabeth Slezak Super Center for Cardiac Research and Biomedical Engineering at Tel Aviv University, the Zimin Institute for Engineering

Solutions Advancing Better Lives, and the Tel Aviv University Center for Combating Pandemics.

Conflicts of Interest: The authors declare no conflict of interest.

Abstract

Nanosensors have a central role in recent approaches for molecular recognition in various applications like imaging, drug delivery systems, and phototherapy. Fluorescent nanoparticles are particularly attractive for such tasks owing to their emission signal that can serve as an optical reporter for the location or the environmental properties. Single-walled carbon nanotubes (SWCNTs) fluoresce in the near infra-red part of the spectrum, where biological samples are relatively transparent, and they do not photobleach or blink. These unique optical properties and their biocompatibility make SWCNTs attractive for a variety of biomedical applications. Here we review recent advancements in protein recognition using SWCNTs functionalized with either natural recognition moieties or synthetic heteropolymers. We emphasize the benefits of the versatile applicability of the SWCNTs sensors in different systems ranging from single-molecule level to *in vivo* sensing in whole animal models. Finally, we discuss the challenges, opportunities, and future perspectives.

Keywords

Molecular Recognition; Fluorescent Nanoparticles; Single-Walled Carbon Nanotubes; Protein Detection; Nanosensors

Introduction

Molecular recognition of DNA, proteins, or viruses, is of extreme importance across many fields of research, especially for the study of the underlying mechanism of biological processes, healthcare, agriculture, food security, and environmental sciences [1–3]. Nanosensors play a key role in current sensing technologies, enabling a deeper understanding of previously unstudied biological phenomena [4–7]. Recent

developments of novel nanosensors offer promising approaches for improved clinical diagnostics and treatments, with increasing interest in nanomaterials-based biosensors [8–18]. A sensor must have two functionalities, namely, target recognition and signal-transduction, which translates the recognition into a measurable signal. For recognition, a sensor can utilize antibodies, aptamers, DNA-sequences, molecular imprints, lectins, or synthetic moieties [19–24]. Signal-transduction, on the other hand, is usually achieved by labeling with fluorescent dyes or gold nanoparticles for immunohistochemistry and other approaches, providing an optical indication of target binding [25–30]. The combination of the recognition with the signal transduction contributes to the sensitivity and selectivity of the sensor in biological environments [31–33]. Various nanoparticles have shown potential to be highly sensitive and selective like metal nanoparticles, quantum dots, nanowires, graphene, graphene quantum dots, and carbon nanotubes [8,9,11,12,31,34], such that they can bind and detect biologically-relevant concentrations of the target analyte. Among the numerous nanosensor platforms, the use of carbon nanotubes as sensors for biotechnological and biomedical applications is of particular interest due to their electrical and thermal properties, mechanical durability, and the ability for further functionalization, doping, and chemical modification [35]. Carbon nanotubes can be divided into two main categories according to the number of cylindrical graphene layers, namely single-walled carbon nanotubes (SWCNTs) and multi-walled carbon nanotubes (MWCNTs). While SWCNTs consist of a single one-atom-thick graphene sheets rolled to form a cylinder with a diameter between 0.7 and 3 nm, MWCNTs consist of several concentric SWCNTs layers whose diameter can range from approximately 1.5 nm for double-walled carbon nanotubes [36] up to 220 nm for tens of layers [35].

In this review, we focus on SWCNTs nanobiosensors owing to their unique physical, chemical, and optical properties [37–40]. We briefly survey SWCNTs properties and the variety of their biomedical applications, and then introduce different methods for recognizing proteins by using their natural substrate, like a protein receptor, a protein-binding partner, an antibody, or an aptamer, or by using a non-biological synthetic substrate bound

to the SWCNT surface. We focus on the approach of utilizing synthetic recognition sites on the nanotubes to detect different proteins. These proteins do not have any affinity to the synthetic substrate, but rather to its pinned configuration when wrapped around the SWCNT scaffold. Finally, we compare and contrast SWCNTs sensors and other sensing platforms, proving a perspective on future direction.

Single-Walled Carbon Nanotubes SWCNTs Properties

SWCNTs are one-atom-thick graphene sheets rolled to form a cylinder with a specific chirality and dimension [6] that determine their physical, chemical, electronic and optical properties [6,10,31,41,42] (Figure 1a-b). The roll up vector, which connects two lattice points on the sp² hybridized graphene sheet, ends up as the circumference of the SWCNT and defines the orientation of the honeycomb lattice of the nanotube. Larger diameter nanotubes have high persistence length [43], and smaller level spacings in their electronic density of states [44] which in turn affects the optical transitions [45]. The nanotubes lattice structure further determines the chemical interaction of the SWCNTs with adsorbed surfactants or polymers, thereby enabling chirality-based separation and sorting [46–48].

Having a diameter of the order of 1 nm, and length in the range of 100 nm up to several micrometers, SWCNTs are one-dimensional, high-aspect-ratio nanocarbon materials, with high surface area that can be readily functionalized. Without surface functionalization, SWCNTs are hydrophobic and tend to bundle due to strong Van der Waals attraction forces [49]. In order to form a colloidal suspension of individually dispersed SWCNTs, they are usually non-covalently functionalized with amphiphilic molecules or polymers by sonication [10,49–53]. Proper surface functionalization can render them biocompatible and thus suitable for numerous biomedical application, including sensing, drug delivery, nanoinjection, phototherapy, imaging, or artificial actuation [14,31,52,54–75].

The high surface to volume ratio can facilitate relatively large cargo load on SWCNTs for efficient delivery applications. For example, SWCNTs can function as universal drug delivery system (DDS) for small interfering RNA (siRNA) and other oligonucleotides, having circulation times ranging from minutes to hours. The delivery of siRNA have been observed to include pharmacokinetics, toxicity, antitumor activity, and target protein knockdown in several cell lines [76]. Besides, SWCNTs can penetrate cells and release siRNA into the cytoplasm [50], which is of great importance for gene silencing applications. Moreover, recent studies have reported the utilization of carbon nanotubes for unassisted delivery of plasmid DNA and siRNA into a variety of model and non-model plant species [77–80].

Semiconducting SWCNTs have unique optical properties, including bright fluorescence emission in the near-infrared (nIR) spectral range mainly between 900 nm to 1600 nm, as well as a broad absorption spectrum compared to organic molecules [81]. In addition, they do not photobleach or blink [16] (Figure 1c). The photostable nIR fluorescence, along with their robust functionalization allow for prolonged detection of SWCNTs through biological samples like tissues, blood, and cells as they are transparent in this spectral range [16,31,42,52,63,67,82–89] (Figure 1d). Human blood, for instance, has a narrow optical transparency window from 900 to 1400 nm where light can penetrate for approximately 3-5 cm deep [90]. Only a few conventional markers absorb or emit strongly in this region, however, some suffer from low photochemical stability or poor biocompatibility [52,91] (Figure 1c). In addition to the optical properties, the physical dimensions of SWCNTs in the order of nanometers to a few microns matches the typical size of biological molecules, enabling precise targeting and visualization [31]. Thus, SWCNTs are attractive candidates for biomedical imaging, detection, and sensing applications.




Figure 1: SWCNTs properties. (a) A graphene sheet segment with indexed lattice points. A nanotube with a chiral indexes (n,m) is obtained by rolling the sheet along a roll-up vector originating at $(0,0)$ up to (n,m) . The chiral angle α (from 0 to 30°) is measured between the roll-up vector and the horizontal zigzag axis; the tube circumference is the length of the roll-up vector. Nanotubes with chiral indexes for which $\text{mod}(n,m) = 0$ are metallic, whereas the rest are semi-conducting. (b) The density of electronic states for a single semi-conducting single-walled carbon nanotube structure. Solid arrows depict the excitation and emission transitions of interest; dashed arrows denote nonradiative relaxation of the electrons (in the conduction band) and holes (in the valence band). (c) Most fluorophores, such as indocyanine green (ICG), undergo rapid photobleaching upon continuous illumination (blue). SWCNT emission (red) remains photostable even under high fluence irradiation ($1.3 \times 10^7 \text{ W m}^{-2}$). (d) SWCNTs fluoresce (blue) primarily in the near-infrared regime ($900\text{--}1600 \text{ nm}$), where Blood (red) and water (black) absorbance is minimal. The gap in tissue absorbance, which occurs in the near-infrared regime, ensures minimal tissue interference with SWCNT fluorescence emission. The figure includes tissue data adapted from Wray and co-workers [90]. Reprinted with permission from Boghossian et al. [16] used with permission from Wiley publication (e) Excitation–emission profile of polymer-functionalized SWCNT suspension. Reprinted with permission from Bisker et al. [92], used with permission from Nature Communications.

SWCNTs as Optical Sensors

The fluorescence signal of SWCNTs is sensitive to the environment and can be affected from global changes in pH and ionic strength [93] or local changes in the surface functionalization or even single-molecule adsorption [94]. The surface functionalization forms a corona phase surrounding the nanotube scaffold, which mediates the interaction of the

SWCNT with molecular analytes in its proximity, and thus determines the fluorescence modulation upon surface binding. The SWCNT fluorescence originates from radiative recombination of excitons, which have strong binding energies [16]. Upon target binding, there are several mechanisms that can lead to the modulation of the emitted light, including exciton quenching due to competitive non-radiative decay, a shift in the Fermi level leading to absorption bleaching, and reorientations of the solvent dipole moments in the close proximity of the SWCNT due to the conformational changes of the corona phase, resulting in a solvatochromic shift [95,96].

Hence, SWCNTs can be used for sensing applications as fluorescence signal transducers, with the benefits of high photostability, lack of photobleaching, and physical size comparable to the typical size of target bio-molecules [31,50]. The various chiralities can enable multiplexed detection by monitoring the emission in different wavelength channels (Figure 1e) in parallel, facilitating high throughput screening [6] and hyperspectral imaging [97]. Further, different chiralities within the same SWCNTs suspension can respond differently to a target analyte owing to the differences in the chemical interactions between the wrapping polymer and the underlying lattice structure of the nanotube [98].

Owing to their unique optical properties, SWCNTs have been utilized as optical sensors for human diseases including different types of cancer [40], glucose levels in diabetics and H₂O₂ in reactive oxygen signaling pathways [82,99–101]. SWCNTs functionalized with nucleic acids or peptides form stable complexes even in complex biological environments [47,102–107], with increased thermal stability up to 200°C [108]. Moreover, SWCNTs functionalized with DNA sequences containing an endonuclease recognition site have been successfully used to study restriction enzyme activity by monitoring their fluorescence emission [109]. DNA-SWCNTs showed increase fluorescence intensity in response to neurotransmitters and have successfully detected dopamine efflux in neuroprogenitor cell culture [110–113] and in acute brain slices [114,115]. (GT)₆-SWCNT has successfully detected

dopamine and norepinephrine in a broad range of pH and salt concentrations, suggesting potential compatibility for *in-vivo* neurophysiology use [116,117]. A recent study demonstrated the recognition of the neurotransmitter serotonin using SWCNTs wrapped with a serotonin-aptamer. This nanosensor was immobilized on a glass surface, on which human blood platelets were cultured, and were shown to detect serotonin release patterns from the cells in real-time [118]. DNA wrapped SWCNTs were also utilized for the detection of single-stranded RNA genome of intact HIV particle [119] and of Doxorubicin, a chemotherapy drug effective against dividing cells due to its affinity to DNA [120]. Further, DNA-SWCNTs were engineered to quantify microRNA hybridization, by a solvatochromism-like response following DNA displacement from the nanotubes surface [121]. In addition, SWCNTs functionalized with boronic acid-modified dextran, polyethylene-glycol (PEG) brush, and rhodamine isothiocyanate functionalized-PEG were shown to be selective sensors for the small molecules riboflavin, L-thyroxine, and estradiol, respectively [122]. Random copolymers consisting of acrylic acid, styrene, and acrylated cortisol, were used to suspend SWCNT, and to demonstrate the detection of human steroid hormones [123]. SWCNT functionalized with a mixture of peptides was shown to detect odor molecules [124] and acetic acid in gaseous phase [125]. Furthermore, dendron-polymer hybrids were utilized as tailorable SWCNT coronae for the detection and real-time monitoring of enzymatic activity [126]. Recently, a sensor for the oncometabolite D-2-hydroxyglutarate (D2HG) was discovered, using (ATTT)7-SWCNT, showing a fluorescence intensity increase in response to D2HG [127].

Protein Recognition with SWCNTs

The recognition of large bio-macromolecules poses a different challenge owing to the size, complexity, and various conformation of the target, as in the case of proteins [128]. Nevertheless, SWCNTs have been successfully utilized for protein detection or for the study of protein-protein interaction by surface functionalization by either natural substrates or synthetic ones [129,130].

Natural Protein Recognition

One approach for protein detection is to use the natural binding partner of the target protein as a recognition site bound to the SWCNTs. This can be achieved, for example, by using an antibody, an aptamer, or a DNA recognition sequence, in order to exploit the original protein-protein or protein-DNA interactions for sensing applications.

A label-free detection was demonstrated in Ahn et al. [131], with nanotubes functionalized with chitosan polymer modified with nitrilotriacetic acid (NTA) chelator. The chitosan was utilized owing to the accessibility of functional groups available for additional modification. The NTA chelated Ni^{2+} and served as proximity quencher modulating the SWCNT fluorescence intensity as a function of distance (Figure 2a). The NTA- Ni^{2+} group can bind to any hexahistidine tagged (his-tag) capture protein, which serves as a natural binding site for the protein of interest. For example, a his-tagged protein A bound to the NTA- Ni^{2+} group was used to capture human immunoglobulin G (IgG) [132]. A subsequent binding of the target protein leads to a modulation of the fluorescence intensity, enabling studying protein-protein interactions, protein glycoprofiles, and protein quantification [31,131–133].




Figure 2: Detecting protein-protein interaction using SWCNTs. (a) Schematic of label-free protein sensor array with fluorescent single-walled carbon nanotubes. SWCNT suspension was spotted on a glass and functionalized with NTA- Ni^{2+} to bind his-tagged capture proteins and detect the interaction between the capture protein and a target protein. The his-tagged capture proteins were first immobilized by the NTA- Ni^{2+} groups through their his-tag residue. Subsequently, upon the addition of a target protein to each spot and its binding to the corresponding capture protein, the distance between the Ni^{2+} quencher and the SWCNT surface changed, resulting in a fluorescence

modulation. Reprinted with permission from Ahn *et al.* [131], Copyright 2011 American Chemical Society. (b) Illustration of the Anti-uPA-DNA-SWCNT complexes. Reprinted with permission from Williams *et al.* [134]. Copyright 2018 American Chemical Society.

Satishkumar *et al.* [135] used fluorescent SWCNT sensors for the detection of avidin by conjugating redox-active dyes bound to a recognition element, biotin, to the SWCNT surface. The biotinylated dyes were quenched while absorbed onto the SWCNT, such that avidin binding resulted in their desorption from the nanotubes and the recovery of the fluorescence. The mechanism of the fluorescence quenching relies on oxidative charge-transfer reactions with small redox-active organic dye molecules [31]. This concept, of dye-ligand complex conjugated to SWCNT, can be highly versatile for a wide range of bioanalytes, through the choice of the specific receptor group attached to the quenched dye [135].

Additional studies showed the detection of the prostate cancer biomarker, urokinase plasminogen activator (uPA), using DNA-SWCNTs conjugated to an anti-uPA antibody (Figure 2b) [134], the detection of single RAP1 proteins secreted from individual *E. coli* cells using SWCNTs functionalized with the RAP1 aptamer [136], and the detection of the SARS-CoV-2 spike protein using SWCNTs functionalized by the ACE2 receptor [137]. Further, Lee *et. al.* demonstrated the optical detection of insulin and platelet-derived growth factor with the corresponding aptamers through two distinct mechanisms, namely, direct protein binding to the aptamer-SWCNT complex, or the detachment of the aptamer from the SWCNTs surface following protein binding, both leading to a decrease in the fluorescent intensity [138]. Moreover, SWCNTs functionalized with HE4 antibody showed a nanomolar sensitivity for HE4, a biomarker for high-grade ovarian carcinoma, enabling noninvasive optical detection of cancer biomarkers [139], and peptide-functionalized SWCNT was used to detect abnormal trypsin activity in urine samples, which is typical in pancreatitis [140].

Synthetic Protein Recognition

Molecular recognition can also be achieved using a synthetic SWCNT corona [122]. In this approach, a synthetic amphiphilic polymer is absorbed onto the hydrophobic surface of the SWCNT. The hydrophobic domains of the polymer form a stable polymer-nanotube complex, whereas the hydrophilic regions extend into the aqueous environment (Figure 3a). The confirmation of the amphiphilic polymer, i.e. the corona phase, can enable the binding of a specific analyte (Figure 3b). In order to discover new corona phases for molecular recognition a library of polymer-conjugated SWCNT was screened against a panel of analytes, while the nIR fluorescence emission was monitored for intensity changes or wavelength shifts (Figure 3c) [92,122,141,142]. A successful screen resulted in a corona phase that can specifically and electively recognize a target analyte [122]. In parallel, theoretical efforts have led to preliminary design principles of a specific configuration of a short polymer wrapping that would recognize the contour and functional groups of a small molecule or a protein of interest [143].

The interaction between the target analyte and the functionalized SWCNTs, as well as the resulting fluorescent modulation, depend on many factors including the nanotube chirality, the composition and valency of the polymer corona, as well as the lipophilicity and redox potential of the target [61,98,110,132,144]. The molecular interaction mediated by the SWCNT corona is an active area of research, where experimental and numerical tools are rapidly being developed in order to shed light on the underlying mechanism of this complex interaction [98,143–147].

The first high-throughput screening of synthetic polymer coronae of SWCNTs targeted small molecules library [122]. Subsequently, the first protein-targeted coronae phase screen has led to the discovery of a sensor for the protein fibrinogen [92]. In this study, 20 SWCNT corona phases were screened against a protein library consisting of 14 proteins from the whole human blood, either the most abundant or of clinical significance, including albumin, transferrin, haptoglobin, fibrinogen, α_1 -

antitrypsin, α_1 -acidglycoprotein (hCG), α_2 -macroglobulin, Immunoglobulin (IgA), IgG, IgM, C-reactive protein (CRP), and insulin [92]. The screen revealed a specific sensor for fibrinogen, using dipalmitoyl-phosphatidylethanolamine (DPPE)-PEG (5kDa) corona (Figure 3d). Fibrinogen is one of the most abundant proteins in the plasma, with an elongated structure that consists of three globular domains connected by coiled-coiled helical chains [148,149]. Fibrinogen detection was also demonstrated in competitive assays in the presence of albumin, which is usually used as a nonspecific binding agent [150–152], or in serum environment. Nonselective parameters such as the molecular weight and hydrophobicity of the proteins, or the surface coverage of the polymer, showed no correlation with the fluorescence response, supporting the hypothesis that the combination of the three-dimensional structure of the target protein along with the conformation of the phospholipid-PEG(5000) corona adopted when pinned around the nanotubes, is a key factor in the successful molecular recognition [92].




Figure 3: Corona phase molecular recognition high-throughput screening. (a) A heteropolymer is adsorbed onto the surface of the SWCNT to form a corona phase around the nanotube. (b) The corona facilitates the recognition of a specific analyte, (c) resulting in a fluorescence emission modulation signature for sensing applications. From Landry *et al.* [146], used with permission from

Sensors. (d) Heat map of the normalized response of the SWCNTs fluorescence intensity to the various proteins. From Bisker *et al.* [92], used with permission from Nature Communications. (e) Binding isotherm for the titration of C₁₆-PEG(2000 Da)-ceramide into insulin solution (blue circles) or PBS (red squares) plotted against the molar ratio of C₁₆-PEG(2000 Da)-ceramide to insulin. The overlapping curves of the injections into insulin or PBS indicate that the released heat in both cases is similar, indicating the lack of affinity between insulin and C₁₆-PEG(2000 Da)-ceramide without the presence of the nanotube interface. Reprinted with permission from Bisker *et al.* [141]. Copyright 2018 American Chemical Society. (f) A proposed albumin recognition model by the carboxylate-rich, hydrophobic polymer, potentially due to mimicking the head group of fatty acids that bind albumin through salt bridges or hydrogen bonds. Reprinted from Budhathoki-Uprety *et al.* [153], used with permission from Nature Communications. (g) Peptoid-SWCNT complexes for protein recognition. An “anchor” region of the peptoid adsorbs to the SWCNT surface, whereas a flanking loop segment interacts with the target protein resulting in a fluorescence modulation. Reprinted from Chio *et al.* [154]. Copyright 2019 American Chemical Society.

An extended corona phase screen against the same protein panel revealed a sensor for insulin [141]. Insulin is a small peptide hormone which plays a key role in blood glucose regulation [155]. Through the secretion of insulin, the pancreas stimulates glucose uptake in order to synthesize lipids, as well as inhibits the production of ketone bodies and the breakdown of proteins, glycogen, and lipids [156]. The high-throughput corona phase screen was done with PEGylated-lipids-SWCNTs, where the C₁₆-PEG200-ceramide-SWCNT complex showed specific and selective quenching response to insulin. The corona phase showed no prior affinity towards insulin, validated using isothermal titration calorimetry, by comparing the heat released while injecting the C₁₆-PEG200-ceramide into insulin solution or PBS (Figure 3e) [141]. The C₁₆-PEG200-ceramide-SWCNT insulin sensor was utilized for detecting insulin secreted from pancreatic β -cells in real-time following a glucose stimulus [157]. The new synthetic nIR fluorescent nanoparticle, paves the way to real-time detection of insulin levels in-vivo using an encapsulating implant [18,31,56,63,86,158,159]. Inference of insulin levels in the various body compartments can be then achieved using a pharmacokinetic modeling of insulin, glucose, and glucagon metabolism [56,160].

In a recent study, Budhathoki-Uprety *et al.* developed an albumin nanosensor using SWCNTs functionalized with

polycarbodiimides polymers incorporating phenyl rings, which mimic fatty acid binding to the albumin [153]. The albumin detection was demonstrated in minimally processed urine samples of microalbuminuria patients under ambient conditions, with similar sensitivity compared to antibody-based clinical assay, suggesting that this antibody-free detection can facilitate diagnosis in point-of-care and resource-limited settings (Figure 3f) [153]. A different approach for protein recognition was demonstrated by Chio *et al.* using peptoids functionalized SWCNT [154]. Peptoids are easy to manufacture and they are resistant to proteases activity. Further, they were shown to specifically recognize enzymes and proteins [161,162]. In their study, Chio *et al.* utilized an anchor-loop peptoids corona for the recognition of the lectin protein wheat germ agglutinin (WGA), and further validated that the WGA kept its functionality of binding to the lectin's target sugars (Figure 3g) [154]. Finally, a high-throughput screening assay has led to the discovery of lipid-PEG functionalized SWCNT as sensors for the nucleocapsid and spike proteins of SARS-CoV-2 [163].

SWCNTs Advantages

Traditional recognition methods use antibodies to identify small and macromolecule targets. Antibody-antigen pairs have a wide range of application ranging from diagnostics and therapeutics to basic and clinical research [164,165]. Although they benefit from high selectivity and specificity to the antigen, a major limitation of antibodies in high-throughput research is the need for injecting the antigen into an animal as the first step of production [166].

Protein corona phase molecular recognition using SWCNT offers an alternative approach for various assays in which degradation, stability, cost, and production scale prevent natural recognition elements, like antibodies, from being employed. In this method, the synthetic polymer used for the recognition does not necessarily have any prior affinity to the target protein, but rather its pinned configuration upon wrapping the nanotube surface forms a conformational binding site. A discovery of such nanosensors can be driven by high throughput screening with

rapid manufacturing processes [122]. This can generate synthetic, non-biological antibody analogs that can overcome some of the limitations of the conventional ones including long development times, high production costs, the need for a living organism for initial production, challenging reproducibility, poor stability due to hydrolysis in ambient temperature resulting in limited shelf time, and sensitivity to degradation while circulating *in-vivo* [167–169]. In contrast, SWCNTs demonstrated long-term stability *in vivo* [63] and were shown to protect DNA or siRNA from cellular nuclease degradation [50,170]. Hence, SWCNT recognition offers a stable and reproducible construct that can push forward discovery research in the field [18,92,122].

SWCNTs fluorescence have several advantages over common organic fluorescent dyes and fluorescent quantum dots (QDs). The main limitation of organic fluorophores is the inevitable photobleaching that restrict their utilization for real-time microscopy experiments lasting several hours [52,171]. Further, organic fluorophores are quenched when jointly applied with hematoxylin and eosin (H&E), an important stain used for evaluation of histological sections [172–174]. QDs are attractive probes for microscopy and imaging, owing to their photophysical properties, including their photostability and the narrow bandwidth fluorescence emission with a wide excitation range [175]. They are mainly used as inert markers [176–181] and FRET-based sensors [182] for both *in vitro* and *in vivo* applications. QDs are highly luminescent semiconducting nanoparticles, and approximately 100 times more resistant to photobleaching than organic fluorophore. Nevertheless, they suffer from signal attenuation under prolonged excitation, fluorescence blinking, complicated surface chemistry, and potential heavy-metal long-term toxicity [183–186]. SWCNTs overcome these limitations owing to their inherent non-photobleaching, non-blinking fluorescence, and their sp^2 hybridized all-carbon structure that gives rise to easy surface functionalization and biocompatibility [14,63,187]. Hence, SWCNTs are subjected to intensive research in many emerging applications of optical nanosensors that exploit their nIR

fluorescent emission and surface chemistry for target recognition and signal transduction [10,16,192–196,31,42,51,67,188–191].

Conclusions

This review provides a summary and a perspective on the utilization of SWCNTs for biosensing applications. The non-photobleaching, non-blinking fluorescent emission of SWCNTs plays a key role in rendering them optical sensors, enabling *in situ*, label-free, real-time detection with both spatial and temporal resolution [92,116,118]. Recent studies have demonstrated the detection of proteins using various approaches for surface functionalization including natural substrates [54,131,135] or synthetic polymers [92,141,153], with the potential to enable long-term continuous monitoring of important biomarkers or to replace costly and time consuming laboratory testing [197]. We have highlighted the advantages of SWCNTs for *in-vivo* and *in-vitro* biomedical applications such as drug delivery, imaging [198], and sensing, focusing on protein recognition. Their considerable potential to advance research and applications in this field has drawn increasing attention in recent years, opening new avenues for future discoveries [18].

In summary, the unique properties of SWCNTs make them excellent candidates for sensing proteins and bi-macromolecules, with optical signal transduction, where advancements in nanotechnology design, synthesis, characterization, and modeling will continue to push forward the discovery of new SWCNT-based fluorescent sensors.

References

1. P Dervan. Molecular recognition of DNA by small molecules. *Bioorg. Med. Chem.* 2001; 9: 2215–2235.
2. S Mann. Molecular recognition in biomineralization, *Nature.* 1988; 332: 119–124.
3. J Rebek. Molecular Recognition with Model Systems. *Angew. Chemie Int. Ed. English.* 1990; 29: 245–255.
4. JN Anker, WP Hall, O Lyandres, NC Shah, J Zhao, et al. Biosensing with plasmonic nanosensors, in: *Nanosci.*

- Technol. A Collect. Rev. from Nat. Journals. UK: Co-Published with Macmillan Publishers Ltd. 2009; 308–319.
5. G Rong, SR Corrie, HA Clark. In Vivo Biosensing: Progress and Perspectives. ACS Sensors. 2017; 2: 327–338.
 6. C Farrera, F Torres Andón, N Feliu, FT Ando, N Feliu, et al. Carbon Nanotubes as Optical Sensors in Biomedicine. ACS Nano. 2017; 11: 10637–10643.
 7. U Drechsler, B Erdogan, VM Rotello. Nanoparticles: Scaffolds for molecular recognition. Chem. - A Eur. J. 2004; 10: 5570–5579.
 8. L Shao, Y Gao, F Yan. Semiconductor quantum dots for Biomedical applications. Sensors (Basel). 2011; 11: 11736–11751.
 9. NS Ramgir, Y Yang, M Zacharias. Nanowire-Based Sensors. Small. 2010; 6: 1705–1722.
 10. Z Chen, X Zhang, R Yang, Z Zhu, Y Chen, et al. Single-walled carbon nanotubes as optical materials for biosensing, Nanoscale. 2011; 3: 1949.
 11. Y Liu, X Dong, P Chen. Biological and chemical sensors based on graphene materials, Chem. Soc. Rev. 2012; 41: 2283–2307.
 12. J Shen, Y Zhu, X Yang, C Li. Graphene quantum dots: Emergent nanolights for bioimaging, sensors, catalysis and photovoltaic devices. Chem. Commun. 2012; 48: 3686–3699.
 13. C Gao, Z Guo, JH Liu, XJ Huang. The new age of carbon nanotubes: An updated review of functionalized carbon nanotubes in electrochemical sensors. Nanoscale. 2012; 4: 1948.
 14. Z Liu, S Tabakman, K Welsher, H Dai. Carbon nanotubes in biology and medicine: In vitro and in vivo detection, imaging and drug delivery. Nano Res. 2009; 2: 85–120.
 15. W Yang, KR Ratinac, SR Ringer, P Thordarson, JJ Gooding, et al. Carbon nanomaterials in biosensors: Should you use nanotubes or graphene. Angew. Chemie - Int. Ed. 2010; 49: 2114–2138.
 16. AA Boghossian, J Zhang, PW Barone, NF Reuel, JH Kim, et al. Near-infrared fluorescent sensors based on single-walled carbon nanotubes for life sciences applications. ChemSusChem. 2011; 4: 848-863.

17. SJJ Kim, SJJ Choi, JSS Jang, HJJ Cho, IDD Kim. Innovative Nanosensor for Disease Diagnosis. *Acc. Chem. Res.* 2017; 50: 1587–1596.
18. MM Alvarez, J Aizenberg, M Analoui, AM Andrews, G Bisker, et al. Emerging Trends in Micro- and Nanoscale Technologies in Medicine: From Basic Discoveries to Translation, *ACS Nano.* 2017; 11: 5195–5214.
19. RM Cooper, DC Leslie, K Domansky, A Jain, C Yung, et al. A microdevice for rapid optical detection of magnetically captured rare blood pathogens. *Lab Chip.* 2014; 14: 182–188.
20. G Köhler, C Milstein. Continuous cultures of fused cells secreting antibody of predefined specificity. *Nature.* 1975; 256: 495–497.
21. D Proske, M Blank, R Buhmann, A Resch. Aptamers - Basic research, drug development, and clinical applications. *Appl. Microbiol. Biotechnol.* 2005; 69: 367–374.
22. JM Morales, CG Skipwith, HA Clark. Quadruplex Integrated DNA:QuID; Nanosensors for Monitoring Dopamine. *Sensors.* 2015; 15: 19912–19924.
23. J Chen, SM Andler, JM Goddard, SR Nugen, VM Rotello. Integrating recognition elements with nanomaterials for bacteria sensing. *Chem. Soc. Rev.* 2017; 46: 1272–1283.
24. D Cai, L Ren, H Zhao, C Xu, L Zhang, et al. A molecular-imprint nanosensor for ultrasensitive detection of proteins. *Nat. Nanotechnol.* 2010; 5: 597-601.
25. RM Warn, L Flegg, A Warn. An investigation of microtubule organization and functions in living *Drosophila* embryos by injection of a fluorescently labeled antibody against tyrosinated alpha-tubulin. *J. Cell Biol.* 1987; 105: 1721–1730.
26. L Sweeny, A Prince, N Patel, LS Moore, EL Rosenthal, et al. Antiangiogenic antibody improves melanoma detection by fluorescently labeled therapeutic antibodies., *Laryngoscope.* 2016; 126: E387–E395.
27. Shimomura, FH Johnson, Y Saiga. Extraction, purification and properties of aequorin, a bioluminescent, *J. Cell. Comp. Physiol.* 1962; 59: 223–239.
28. LE Cole, RD Ross, JM Tilley, T Vargo-Gogola, RK Roeder. Gold nanoparticles as contrast agents in X-ray imaging and

- computed tomography. *Nanomedicine*. 2015; 10: 321–341.
29. AH Coons, HJ Creech, RN Jones. Immunological Properties of an Antibody Containing a Fluorescent Group. *Exp. Biol. Med.* 1941; 47: 200–202.
 30. X Xie, W Zhang, A Abbaspourrad, J Ahn, A Bader, et al. Microfluidic Fabrication of Colloidal Nanomaterials-Encapsulated Microcapsules for Biomolecular Sensing, *Nano Lett.* 2017; 17.
 31. S Kruss, AJ Hilmer, J Zhang, NF Reuel, B Mu, et al. Carbon nanotubes as optical biomedical sensors, *Adv. Drug Deliv. Rev.* 2013; 65: 1933–1950.
 32. HK Hunt, AM Armani. Label-free biological and chemical sensors, *Nanoscale*. 2010; 2: 1544.
 33. WJ Peveler, M Yazdani, VM Rotello. Selectivity and Specificity: Pros and Cons in Sensing. *ACS Sensors*. 2016; 1: 1282–1285.
 34. G Doria, J Conde, B Veigas, L Giestas, C Almeida, et al. Noble metal nanoparticles for biosensing applications, *Sensors*. 2012; 12: 1657–1687.
 35. A Eatemadi, H Daraee, H Karimkhanloo, M Kouhi, N Zarghami, et al. Carbon nanotubes: Properties, synthesis, purification, and medical applications. *Nanoscale Res. Lett.* 2014; 9.
 36. DA Tsyboulski, Y Hou, N Fakhri, S Ghosh, R Zhang, et al. Do inner shells of double-walled carbon nanotubes fluoresce? *Nano Lett.* 2009; 9: 3282–3289.
 37. A Ado, Jorio G. Dresselhaus, M.S. Dresselhaus, Carbon nanotubes: Advanced topics in the synthesis, structure, properties and applications, *Mater. Today*. 2008; 11: 57.
 38. RH Baughman, AA Zakhidov, WA De Heer. Carbon nanotubes - The route toward applications, *Science*: 80-. 2002; 297: 787–792.
 39. Z Li, ALB de Barros, DCF Soares, SN Moss, L Alisaraie. Functionalized single-walled carbon nanotubes: cellular uptake, biodistribution and applications in drug delivery. *Int. J. Pharm.* 2017; 524: 41–54.
 40. B Dineshkumar, K Krishnakumar, A Bhatt, D Paul, J Cherian, et al. Single-walled and multi-walled carbon nanotubes based drug delivery system: Cancer therapy: A review, *Indian J. Cancer*. 2015; 52: 262.

41. PM Ajayan, JC Charlier, AG Rinzler. Carbon nanotubes: From macromolecules to nanotechnology, Proc. Natl. Acad. Sci. U. S. A. 1999; 96: 14199–14200.
42. PW Barone, S Baik, DA Heller, MS Strano. Near-infrared optical sensors based on single-walled carbon nanotubes. Nat. Mater. 2005; 4: 86–92.
43. N Fakhri, DA Tsyboulski, L Cognet, RB Weisman, M Pasquali. Diameter-dependent bending dynamics of single-walled carbon nanotubes in liquids. Proc. Natl. Acad. Sci. 2009; 106: 14219–14223.
44. SM Bachilo, MS Strano, C Kittrell, RH Hauge, RE Smalley, et al. Structure-assigned optical spectra of single-walled carbon nanotubes. Science. 2002; 298: 2361–2366.
45. F Wang. The Optical Resonances in Carbon Nanotubes Arise from Excitons, Science:80-. 2005; 308: 838–841.
46. H Liu, D Nishide, T Tanaka, H Kataura. Large-scale single-chirality separation of single-wall carbon nanotubes by simple gel chromatography. Nat. Commun. 2011; 2.
47. M Zheng, A Jagota, ED Semke, BA Diner, RS Mclean, et al. DNA-assisted dispersion and separation of carbon nanotubes, Nat. Mater. 2003; 2: 338–342.
48. JA Fagan. Aqueous two-polymer phase extraction of single-wall carbon nanotubes using surfactants. Nanoscale Adv. 2019; 1: 3307–3324.
49. VC Moore, MS Strano, EH Haroz, RH Hauge, RE Smalley, et al. Individually Suspended Single-Walled Carbon Nanotubes in Various Surfactants, Nano Lett. 2003; 3: 1379–1382.
50. C Ménard-Moyon, K Kostarelos, M Prato, A Bianco. Functionalized Carbon Nanotubes for Probing and Modulating Molecular Functions. Chem. Biol. 2010; 17: 107–115.
51. AJ Gillen, AA Boghossian. Non-covalent Methods of Engineering Optical Sensors Based on Single-Walled Carbon Nanotubes. Front. Chem. 2019; 7: 612.
52. BDA Heller, S Baik, TE Eurell, MS Strano. Single-Walled Carbon Nanotube Spectroscopy in Live Cells: Towards Long-Term Labels and Optical Sensors. Adv. Mater. 2005; 17: 2793–2799.
53. NE Kallmyer, T Huynh, JC Graves, J Musielewicz, D

- Tamiev, et al. Influence of sonication conditions and wrapping type on yield and fluorescent quality of noncovalently functionalized single-walled carbon nanotubes, *Carbon N. Y.* 2018; 139: 609–613.
54. C Rungnim, T Rungrotmongkol, N Kungwan, S Hannongbua. Protein–protein interactions between SWCNT/chitosan/EGF and EGF receptor: a model of drug delivery system. *J. Biomol. Struct. Dyn.* 2016; 34: 1919–1929.
 55. A Sanginario, B Miccoli, D Demarchi. Carbon Nanotubes as an Effective Opportunity for Cancer Diagnosis and Treatment. *Biosensors.* 2017; 7: 9.
 56. G Bisker, NM Iverson, J Ahn, MS Strano. A pharmacokinetic model of a tissue implantable insulin sensor, *Adv. Healthc. Mater.* 2014; 4: 87–97.
 57. JP Giraldo, MP Landry, SM Faltermeier, TP McNicholas, NM Iverson, et al. Plant nanobionics approach to augment photosynthesis and biochemical sensing. *Nat. Mater.* 2014; 13: 400–408.
 58. MH Wong, JP Giraldo, SY Kwak, VB Koman, R Sinclair, et al. Nitroaromatic detection and infrared communication from wild-type plants using plant nanobionics. *Nat. Mater.* 2016; 16: 264–272.
 59. SF Oliveira, G Bisker, NA Bakh, SL Gibbs, MP Landry, et al. Protein functionalized carbon nanomaterials for biomedical applications. *Carbon N. Y.* 2015; 95: 767–779.
 60. SY Kwak, MH Wong, TTS Lew, G Bisker, MA Lee, et al. Nanosensor Technology Applied to Living Plant Systems, *Annu. Rev. Anal. Chem.* 2017; 10: 113–140.
 61. PV Jena, D Roxbury, TV Galassi, L Akkari, CP Horoszko, et al. A Carbon Nanotube Optical Reporter Maps Endolysosomal Lipid Flux. *ACS Nano.* 2017; 11: 10689–10703.
 62. TV Galassi, PV Jena, J Shah, G Ao, E Molitor, et al. An optical nanoreporter of endolysosomal lipid accumulation reveals enduring effects of diet on hepatic macrophages in vivo, *Sci. Transl. Med.* 2018; 10.
 63. NM Iverson, PW Barone, M Shandell, LJ Trudel, S Sen, et al. In vivo biosensing via tissue-localizable near-infrared-fluorescent single-walled carbon nanotubes. *Nat.*

- Nanotechnol. 2013; 8: 873–880.
64. MA Lee, N Bakh, G Bisker, EN Brown, MS Strano. A Pharmacokinetic Model of a Tissue Implantable Cortisol Sensor. *Adv. Healthc. Mater.* 2016; 5: 3004-3015.
 65. A Bianco, K Kostarelos, M Prato. Applications of carbon nanotubes in drug delivery, *Curr. Opin. Chem. Biol.* 2005; 9: 674–679.
 66. S Vardharajula, SZ Ali, PM Tiwari, EE Eroglu, K Vig, et al. functionalized-carbon-nanotubes--biomedical-applications, *Int. J. Nanomedicine.* 2012; 7: 5361–5374.
 67. AG Godin, JA Varela, Z Gao, N Danné, JP Dupuis, et al. Single-nanotube tracking reveals the nanoscale organization of the extracellular space in the live brain. *Nat. Nanotechnol.* 2017; 12: 238–243.
 68. E Hofferber, J Meier, N Herrera, J Stapleton, C Calkins, et al. Detection of single walled carbon nanotube based sensors in a large mammal. *Nanomedicine Nanotechnology, Biol. Med.* 2021; 102489.
 69. N Sinha, JTW Yeow. Carbon Nanotubes for Biomedical Applications, *IEEE Trans. Nanobioscience.* 2005; 4: 180–195.
 70. X Chen, A Kis, A Zettl, CR Bertozzi. A cell nanoinjector based on carbon nanotubes. *Proc. Natl. Acad. Sci. U. S. A.* 2007; 104: 8218–8222.
 71. K Welsler, Z Liu, SP Sherlock, JT Robinson, Z Chen, et al. A route to brightly fluorescent carbon nanotubes for near-infrared imaging in mice. *Nat. Nanotechnol.* 2009; 4: 773–780.
 72. AE Aliev, O Jiyoung, K Mikhail, AAKS Fang, AF Fonseca, et al. Giant-Stroke, Superelastic Carbon Nanotube Aerogel Muscles, *Science*:80-. 2009; 323: 1575–1578.
 73. V Schroeder, S Savagatrup, M He, S Lin, TM Swager. Carbon nanotube chemical sensors, *Chem. Rev.* 2019; 119: 599–663.
 74. M Hernández-Rivera, NG Zaibaq, LJ Wilson. Toward carbon nanotube-based imaging agents for the clinic, *Biomaterials.* 2016; 101: 229–240.
 75. JP Kim, BY Lee, J Lee, S Hong, SJ Sim. Enhancement of sensitivity and specificity by surface modification of carbon nanotubes in diagnosis of prostate cancer based on carbon

- nanotube field effect transistors. *Biosens. Bioelectron.* 2009; 24: 3372–3378.
76. D Lynn Kirkpatrick, M Weiss, A Naumov, G Bartholomeusz, R Bruce Weisman, et al. Carbon nanotubes: Solution for the therapeutic delivery of siRNA? *Materials.* Basel. 2012; 5: 278–301.
 77. GS Demirer, H Zhang, JL Matos, NS Goh, FJ Cunningham, et al. High aspect ratio nanomaterials enable delivery of functional genetic material without DNA integration in mature plants. *Nat. Nanotechnol.* 2019; 14: 456–464.
 78. SY Kwak, TTS Lew, CJ Sweeney, VB Koman, MH Wong, et al. Chloroplast-selective gene delivery and expression in planta using chitosan-complexed single-walled carbon nanotube carriers, *Nat. Nanotechnol.* 2019; 14: 447–455.
 79. H Wu, R Nißler, V Morris, N Herrmann, P Hu, et al. Monitoring Plant Health with Near-Infrared Fluorescent H₂O₂ Nanosensors. *Nano Lett.* 2020; 20: 2432–2442.
 80. H Zhang, H Zhang, GS Demirer, E González-Grandío, C Fan, et al. Engineering DNA nanostructures for siRNA delivery in plants. *Nat. Protoc.* 2020; 15: 3064–3087.
 81. MJ O’Connell, SM Bachilo, CB Huffman, VC Moore, MS Strano, et al. Band Gap Fluorescence from Individual Single-Walled Carbon Nanotubes, *Science* 80-. 2002; 297: 593–596.
 82. DA Heller, H Jin, BM Martinez, D Patel, BM Miller, et al. Multimodal optical sensing and analyte specificity using single-walled carbon nanotubes. *Nat. Nanotechnol.* 2009; 4: 114–120.
 83. M Gravely, MM Safae, D Roxbury. Biomolecular Functionalization of a Nanomaterial To Control Stability and Retention within Live Cells. *Nano Lett.* 2019; 19: 6203–6212.
 84. Z Gao, N Danné, A Godin, B Lounis, L Cognet. Evaluation of Different Single-Walled Carbon Nanotube Surface Coatings for Single-Particle Tracking Applications in Biological Environments. *Nanomaterials.* 2017; 7: 393.
 85. N Danné, M Kim, AG Godin, H Kwon, Z Gao, et al. Ultrashort Carbon Nanotubes That Fluoresce Brightly in the Near-Infrared, *ACS Nano.* 2018; 12: 6059–6065.

86. NM Iverson, G Bisker, E Farias, V Ivanov, J Ahn, et al. Quantitative Tissue Spectroscopy of Near Infrared Fluorescent Nanosensor Implants. *J. Biomed. Nanotechnol.* 2016; 12: 1035–1047.
87. A Kodym, R Afza. Physical and Chemical Mutagenesis, in: *Plant Funct. Genomics*. New Jersey: Humana Press. 2003; 189–204.
88. R Saito, G Dresselhaus, MS Dresselhaus. *Physical Properties of Carbon Nanotubes*. Singapore: Imperial College Press and Distributed by World Scientific Publishing Co. 1998.
89. DA Heller, ES Jeng, TK Yeung, BM Martinez, AE Moll, et al. Optical detection of DNA conformational polymorphism on single-walled carbon nanotubes. *Science* 80-. 2006; 311: 508–511.
90. S Wray, M Cope, DT Delpy, JS Wyatt, EOR Reynolds. Characterization of the near infrared absorption spectra of cytochrome aa3 and haemoglobin for the non-invasive monitoring of cerebral oxygenation. *BBA - Bioenerg.* 1988; 933: 184-192.
91. AM Smith, S Nie. Chemical analysis and cellular imaging with quantum dots. *Analyst.* 2004; 129: 672.
92. G Bisker, J Dong, HD Park, NM Iverson, J Ahn, et al. Protein-targeted corona phase molecular recognition. *Nat. Commun.* 2016; 7: 1–14.
93. DP Salem, X Gong, AT Liu, VB Koman, J Dong, et al. Ionic Strength-Mediated Phase Transitions of Surface-Adsorbed DNA on Single-Walled Carbon Nanotubes. *J. Am. Chem. Soc.* 2017; 139: 16791–16802.
94. J Zhang, AA Boghossian, PW Barone, A Rwei, JH Kim, et al. Single molecule detection of nitric oxide enabled by d(AT)₁₅ DNA adsorbed to near infrared fluorescent single-walled carbon nanotubes, *J. Am. Chem. Soc.* 2011; 133: 567–581.
95. JH Choi, MS Strano. Solvatochromism in single-walled carbon nanotubes. *Appl. Phys. Lett.*:2007; 90: 223114 - 223114-3.
96. DA Heller, GW Pratt, J Zhang, N Nair, AJ Hansborough, et al. Peptide secondary structure modulates single-walled carbon nanotube fluorescence as a chaperone sensor for nitroaromatics. *Proc. Natl. Acad. Sci. U. S. A.* 2011; 108:

- 8544-8549.
97. D Roxbury, PV Jena, RM Williams, B Enyedi, P Niethammer, et al. Hyperspectral Microscopy of Near-Infrared Fluorescence Enables 17-Chirality Carbon Nanotube Imaging, *Sci. Rep.* 2015; 5: 14167.
 98. DP Salem, MP Landry, G Bisker, J Ahn, S Kruss, et al. Chirality dependent corona phase molecular recognition of DNA-wrapped carbon nanotubes, *Carbon N. Y.* 2016; 97.
 99. H Jin, DA Heller, M Kalbacova, JH Kim, J Zhang, et al. Detection of single-molecule H₂ O₂ signalling from epidermal growth factor receptor using fluorescent single-walled carbon nanotubes, *Nat. Nanotechnol.* 2010; 5: 302–309.
 100. PW Barone, MS Strano. Reversible control of carbon nanotube aggregation for a glucose affinity sensor. *Angew. Chemie - Int. Ed.* 2006; 45: 8138–8141.
 101. Y Lin, F Lu, Y Tu, Z Ren. Glucose Biosensors Based on Carbon Nanotube Nanoelectrode Ensembles. 2004; 4.
 102. X Tang, S Bansaruntip, N Nakayama, E Yenilmez, YI Chang, et al. Carbon nanotube DNA sensor and sensing mechanism. *Nano Lett.* 2006; 6: 1632–1636.
 103. R Nißler, FA Mann, P Chaturvedi, J Horlebein, D Meyer, et al. Quantification of the Number of Adsorbed DNA Molecules on Single-Walled Carbon Nanotubes. *J. Phys. Chem. C.* 2019; 123: 4837–4847.
 104. Z Zhu, R Yang, M You, X Zhang, Y Wu, et al. Single-walled carbon nanotube as an effective quencher, *Anal. Bioanal. Chem.* 2010; 396: 73–83.
 105. HM So, K Won, Y Hwan Kim, BK Kim, B Hwan Ryu, et al. Single-Walled Carbon Nanotube Biosensors Using Aptamers as Molecular Recognition Elements. *J. AM. CHEM. SOC.* 2005; 127: 11906–11907.
 106. D Pantarotto, CD Partidos, J Hoebeke, F Brown, E Kramer, et al. Immunization with peptide-functionalized carbon nanotubes enhances virus-specific neutralizing antibody responses, *Chem. Biol.* 2003; 10: 961–966.
 107. S Wang, ES Humphreys, SY Chung, DF Delduco, SR Lustig, et al. Peptides with selective affinity for carbon nanotubes, *Nat. Mater.* 2003; 2: 196–200.
 108. MM Safaee, M Gravely, A Lamothe, M McSweeney, D

- Roxbury. Enhancing the Thermal Stability of Carbon Nanomaterials with DNA. *Sci. Rep.* 2019; 9: 11926.
109. SJ Wu, N Schuergers, KH Lin, AJ Gillen, C Corminboeuf, et al. Restriction Enzyme Analysis of Double-Stranded DNA on Pristine Single-Walled Carbon Nanotubes. *ACS Appl. Mater. Interfaces.* 2018; 10: 22.
 110. E Polo, S Kruss. Impact of Redox-Active Molecules on the Fluorescence of Polymer-Wrapped Carbon Nanotubes. *J. Phys. Chem. C.* 2016; 120: 3061–3070.
 111. S Kruss, MP Landry, E Vander Ende, BMA Lima, NF Reuel, et al. Neurotransmitter detection using corona phase molecular recognition on fluorescent single-walled carbon nanotube sensors. *J. Am. Chem. Soc.* 2014; 136: 713–724.
 112. FA Mann, N Herrmann, D Meyer, S Kruss. Tuning selectivity of fluorescent carbon nanotube-based neurotransmitter sensors. *Sensors.* 2017; 17.
 113. E Polo, S Kruss. Nanosensors for neurotransmitters. *Anal. Bioanal. Chem.* 2016; 408: 2727–2741.
 114. JTD Del Bonis-O'Donnell, RH Page, AG Beyene, EG Tindall, IR McFarlane, et al. Dual Near-Infrared Two-Photon Microscopy for Deep-Tissue Dopamine Nanosensor Imaging, *Adv. Funct. Mater.* 2017; 27: 1702112.
 115. AG Beyene, K Delevich, JT Del Bonis-O'Donnell, DJ Piekarski, WC Lin, et al. Imaging striatal dopamine release using a nongenetically encoded near infrared fluorescent catecholamine nanosensor, *Sci. Adv.* 2019; 5: eaaw3108.
 116. AG Beyene, K Delevich, SJ Yang, MP Landry. New Optical Probes Bring Dopamine to Light. *Biochemistry.* 2018; 57: 6379–6381.
 117. AG Beyene, AA Alizadehmojarad, G Dorlhiac, N Goh, AM Streets, et al. Ultralarge Modulation of Fluorescence by Neuromodulators in Carbon Nanotubes Functionalized with Self-Assembled Oligonucleotide Rings. *Nano Lett.* 2018; 18: 6995–7003.
 118. M Dinarvand, E Neubert, D Meyer, G Selvaggio, FA Mann, et al. Near-Infrared Imaging of Serotonin Release from Cells with Fluorescent Nanosensors. *Nano Lett.* 2019; 19: 6604–6611.
 119. JD Harvey, HA Baker, MV Ortiz, A Kentsis, DA Heller. HIV Detection via a Carbon Nanotube RNA Sensor. *ACS*

- Sensors. 2019; 4: 1236–1244.
120. JD Harvey, RM Williams, KM Tully, HA Baker, Y Shamay, et al. An in Vivo Nanosensor Measures Compartmental Doxorubicin Exposure. *Nano Lett.* 2019; 19: 4343–4354.
 121. JD Harvey, PV Jena, HA Baker, GH Zerbe, RM Williams, et al. A carbon nanotube reporter of microRNA hybridization events in vivo. *Nat. Biomed. Eng.* 2017; 1: 0041.
 122. J Zhang, MP Landry, PW Barone, JH Kim, S Lin, et al. Molecular recognition using corona phase complexes made of synthetic polymers adsorbed on carbon nanotubes. *Nat. Nanotechnol.* 2013; 8: 959–968.
 123. MA Lee, S Wang, X Jin, NA Bakh, FT Nguyen, et al. Implantable Nanosensors for Human Steroid Hormone Sensing In Vivo Using a Self-Templating Corona Phase Molecular Recognition, *Adv. Healthc. Mater.* 2020; 9: 2000429.
 124. V Shumeiko, Y Paltiel, G Bisker, Z Hayouka, O Shoseyov. A nanoscale paper-based near-infrared optical nose (NIRON). *Biosens. Bioelectron.* 2021; 172: 112763.
 125. V Shumeiko, E Malach, Y Helman, Y Paltiel, G Bisker, et al. A nanoscale optical biosensor based on peptide encapsulated SWCNTs for detection of acetic acid in the gaseous phase, *Sensors Actuators B Chem.* 2021; 327: 128832.
 126. V Wulf, G Slor, P Rathee, RJ Amir, G Bisker. Dendron–Polymer Hybrids as Tailorable Responsive Coronae of Single-Walled Carbon Nanotubes. *ACS Nano.* acsnano.1c09125, Dec. 2021.
 127. D Amir, A Hendler-Neumark, V Wulf, R Ehrlich, G Bisker. Oncometabolite Fingerprinting Using Fluorescent Single-Walled Carbon Nanotubes. *Adv. Mater. Interfaces.* 2021.
 128. P Chakrabarti, J Janin. Dissecting protein-protein recognition sites. *Proteins Struct. Funct. Genet.* 2002; 47: 334–343.
 129. A Hendler-Neumark, G Bisker. Fluorescent Single-Walled Carbon Nanotubes for Protein Detection, *Sensors.* 2019; 19: 5403.

130. G Bisker. Optical Nanosensors in the Near-Infrared Spectral Window, in: Conf. Lasers Electro-Optics. Washington, D.C.: OSA. 2021: AF2Q.6.
131. JH Ahn, JH Kim, NF Reuel, PW Barone, AA Boghossian, et al. Label-Free, Single Protein Detection on a Near-Infrared Fluorescent Single-Walled Carbon Nanotube/Protein Microarray Fabricated by Cell-Free Synthesis. *Nano Lett.* 2011; 11: 19.
132. JT Nelson, S Kim, NF Reuel, DP Salem, G Bisker, et al. Mechanism of Immobilized Protein A Binding to Immunoglobulin G on Nanosensor Array Surfaces, *Anal. Chem.* 2015; 87: 8186–8193.
133. NF Reuel, JH Ahn, JH Kim, J Zhang, AA Boghossian, et al. Transduction of glycan-lectin binding using near-infrared fluorescent single-walled carbon nanotubes for glycan profiling, *J. Am. Chem. Soc.* 2011; 133: 17923–17933.
134. RM Williams, C Lee, DA Heller. A Fluorescent Carbon Nanotube Sensor Detects the Metastatic Prostate Cancer Biomarker uPA. *ACS Sensors.* 2018; 3: 1838–1845.
135. BC Satishkumar, LO Brown, Y Gao, CCC Wang, HLL Wang, et al. Reversible fluorescence quenching in carbon nanotubes for biomolecular sensing. *Nat. Nanotechnol.* 2007; 2: 560–564.
136. MP Landry, H Ando, AY Chen, J Cao, VI Kottadiel, et al. Single-molecule detection of protein efflux from microorganisms using fluorescent single-walled carbon nanotube sensor arrays, *Nat. Nanotechnol.* 2017; 12: 368–377.
137. RL Pinals, F Ledesma, D Yang, N Navarro, S Jeong, et al. Rapid SARS-CoV-2 Spike Protein Detection by Carbon Nanotube-Based Near-Infrared Nanosensors. *Nano Lett.* 2021; 21: 2272–2280.
138. K Lee, J Lee, B Ahn. Design of Refolding DNA Aptamer on Single-Walled Carbon Nanotubes for Enhanced Optical Detection of Target Proteins. *Anal. Chem.* 2019; 91: 12704–12712.
139. RM Williams, C Lee, TV Galassi, JD Harvey, R Leicher, et al. Noninvasive ovarian cancer biomarker detection via an optical nanosensor implant. *Sci. Adv.* 2018; 4: eaaq1090.
140. V Shumeiko, Y Paltiel, G Bisker, Z Hayouka, O

- Shoseyov. A Paper-Based Near-Infrared Optical Biosensor for Quantitative Detection of Protease Activity Using Peptide-Encapsulated SWCNTs. *Sensors*. 2020; 20: 5247.
141. G Bisker, NA Bakh, MA Lee, J Ahn, M Park, et al. Insulin Detection Using a Corona Phase Molecular Recognition Site on Single-Walled Carbon Nanotubes. *ACS Sensors*. 2018; 8: 367–377.
142. AG Beyene, GS Demirer, MP Landry. Nanoparticle-Templated Molecular Recognition Platforms for Detection of Biological Analytes. In: *Curr. Protoc. Chem. Biol.* Hoboken: John Wiley & Sons, Inc. 2016; 197–223.
143. G Bisker, J Ahn, S Kruss, ZW Ulissi, DP Salem, et al. A mathematical formulation and solution of the CoPhMoRe inverse problem for helically wrapping polymer corona phases on cylindrical substrates. *J. Phys. Chem. C*. 2015; 119: 13876–13886.
144. MP Landry, L Vuković, S Kruss, G Bisker, AM Landry, et al. Comparative Dynamics and Sequence Dependence of DNA and RNA Binding to Single Walled Carbon Nanotubes. *J. Phys. Chem. C*. 2015; 119: 10048–10058.
145. ZW Ulissi, J Zhang, V Sresht, D Blankschtein, MS Strano. 2D Equation-of-State Model for Corona Phase Molecular Recognition on Single-Walled Carbon Nanotube and Graphene Surfaces. *Langmuir*. 2015; 31: 628–636.
146. MP Landry, S Kruss, JT Nelson, G Bisker, NM Iverson, et al. Experimental tools to study molecular recognition within the nanoparticle corona. *Sensors*. 2014; 14: 16196–16211.
147. MM Safaee, M Gravely, C Rocchio, M Simmeth, D Roxbury. DNA Sequence Mediates Apparent Length Distribution in Single-Walled Carbon Nanotubes. *ACS Appl. Mater. Interfaces*. 2019; 11: 2225–2233.
148. IS Yermolenko, VK Lishko, TP Ugarova, SN Magonov. High-Resolution Visualization of Fibrinogen Molecules and Fibrin Fibers with Atomic Force Microscopy. *Biomacromolecules*. 2011; 12: 370–379.
149. HA Scheraga. The thrombin-fibrinogen interaction. *Biophys. Chem*. 2004; 112: 117–130.
150. G Zheng, F Patolsky, Y Cui, WU Wang, CM Lieber. Multiplexed electrical detection of cancer markers with

- nanowire sensor arrays. *Nat. Biotechnol.* 2005; 23: 1294–1301.
151. YL Jeyachandran, E Mielczarski, B Rai, JA Mielczarski. Quantitative and Qualitative Evaluation of Adsorption/Desorption of Bovine Serum Albumin on Hydrophilic and Hydrophobic Surfaces. *Langmuir.* 2009; 25: 11614–11620.
152. B Sweryda-Krawiec, H Devaraj, G Jacob, JJ Hickman. A New Interpretation of Serum Albumin Surface Passivation. *Langmuir.* 2004; 20: 2054–2056.
153. J Budhathoki-Uprety, J Shah, JA Korsen, AE Wayne, TV Galassi, et al. Synthetic molecular recognition nanosensor paint for microalbuminuria. *Nat. Commun.* 2019; 10: 3605.
154. L Chio, JT Del Bonis-O'Donnell, MA Kline, JH Kim, IR McFarlane, et al. Electrostatic Assemblies of Single-Walled Carbon Nanotubes and Sequence-Tunable Peptoid Polymers Detect a Lectin Protein and Its Target Sugars. *Nano Lett.* 2019; 19: 7563–7572.
155. M Vakilian, Y Tahamtani, K Ghaedi. A review on insulin trafficking and exocytosis. *Gene.* 2019; 706: 52–61.
156. P Sonksen, J Sonksen. Insulin: Understanding its action in health and disease. *Br. J. Anaesth.* 2000; 85: 69–79.
157. R Ehrlich, A Hendler-Neumark, V Wulf, D Amir, G Bisker. Optical Nanosensors for Real-Time Feedback on Insulin Secretion by β -Cells. *Small.* 2021; 17: 2101660.
158. JP Giraldo, MP Landry, SY Kwak, RM Jain, MH Wong, et al. A Ratiometric Sensor Using Single Chirality Near-Infrared Fluorescent Carbon Nanotubes: Application to In Vivo Monitoring. *Small.* 2015; 11: 3973–3984.
159. EM Hofferber, JA Stapleton, J Adams, M Kuss, B Duan, et al. Implantable Nanotube Sensor Platform for Rapid Analyte Detection. *Macromol. Biosci.* 2019; 19: 1–8.
160. NA Bakh, G Bisker, MA Lee, X Gong, MS Strano. Rational Design of Glucose-Responsive Insulin Using Pharmacokinetic Modeling. *Adv. Healthc. Mater.* 2017; 6.
161. GK Olivier, A Cho, B Sanii, MD Connolly, H Tran, et al. Antibody-Mimetic Peptoid Nanosheets for Molecular Recognition. *2013 ACS Nano.* 2013; 7: 9276–9286.
162. A Battigelli, JH Kim, DC Dehigasptiya, C Proulx, EJ Robertson, et al. Glycosylated Peptoid Nanosheets as a

- Multivalent Scaffold for Protein Recognition. *ACS Nano*. 2018; 12: 2455–2465
163. SY Cho, X Jin, X Gong, S Yang, J Cui, et al. Antibody-Free Rapid Detection of SARS-CoV-2 Proteins Using Corona Phase Molecular Recognition to Accelerate Development Time. *Anal. Chem.* 2021; 93: 14685–14693.
164. PJ Hudson. Recombinant antibody constructs in cancer therapy. *Curr. Opin. Immunol.* 1999; 11: 548–557.
165. M Trikha, L Yan, MT Nakada. Monoclonal antibodies as therapeutics in oncology. *Curr. Opin. Biotechnol.* 2002; 13: 609–614.
166. SD Jayasena. Aptamers: An emerging class of molecules that rival antibodies in diagnostics. *Clin. Chem.* 1999; 45: 1628–1650.
167. S Miersch, SS Sidhu. Synthetic antibodies: Concepts, potential and practical considerations. *Methods.* 2012; 57: 486–498.
168. SS Sidhu, FA Fellouse. Synthetic therapeutic antibodies. *Nat. Chem. Biol.* 2006; 2: 682–688.
169. JO Mahony, K Nolan, MR Smyth, B Mizaikoff. Molecularly imprinted polymers - Potential and challenges in analytical chemistry. *Anal. Chim. Acta.* 2005; 534: 31-39.
170. Y Wu, JA Phillips, H Liu, R Yang, W Tan. Carbon Nanotubes Protect DNA Strands during Cellular Delivery. *ACS Nano.* 2008; 2: 2023–2028.
171. V Saxena, M Sadoqi, J SHAO. Degradation Kinetics of Somatostatin in Aqueous Solution, *Drug Dev. Ind. Pharm.* 2003; 29: 1027–1033.
172. LP Gartner, JL Hiatt. *Color textbook of histology.* Saunders: Elsevier. 2007.
173. HJ Conn. Progress in the Standardization of Stains the Haematoxylin Problem. *Stain Technol.* 1927; 2: 1–3.
174. WCW Chan, DJ Maxwell, X Gao, RE Bailey, M Han, et al. Luminescent quantum dots for multiplexed biological detection and imaging. *Curr. Opin. Biotechnol.* 2002; 13: 40–46.
175. M Bruchez, M Moronne, P Gin, S Weiss, AP Alivisatos. Semiconductor nanocrystals as fluorescent biological labels. *Science (80-.)*. 1998; 281: 2013–2016.
176. AP Alivisatos, W Gu, C Larabell. Quantum Dots as

- Cellular Probes. *Annu. Rev. Biomed. Eng.* 2005; 7: 55–76.
177. WCW Chan, S Nie. Quantum dot bioconjugates for ultrasensitive nonisotopic detection. *Science* (80-). 1998; 281: 2016–2018.
 178. M Howarth, K Takao, Y Hayashi, AY Ting. Targeting quantum dots to surface proteins in living cells with biotin ligase. *Proc. Natl. Acad. Sci. U. S. A.* 2005; 102: 7583–7588.
 179. JK Jaiswal, H Mattoussi, JM Mauro, SM Simon. Long-term multiple color imaging of live cells using quantum dot bioconjugates. *Nat. Biotechnol.* 2003; 21: 47–51.
 180. S Kim, YT Lim, EG Soltesz, AM De Grand, J Lee, et al. Near-infrared fluorescent type II quantum dots for sentinel lymph node mapping. *Nat. Biotechnol.* 2004; 22: 93–97.
 181. X Michalet. Quantum Dots for Live Cells, in Vivo Imaging, and Diagnostics. *Science* (80-). 2005; 307: 538–544.
 182. JM Dubach, DI Harjes, HA Clark. Ion-Selective Nanoptodes Incorporating Quantum Dots. *J. Am. Chem. Soc.* 2007; 8418–8419.
 183. P Cherukuri, SM Bachilo, SH Litovsky, RB Weisman. Near-infrared fluorescence microscopy of single-walled carbon nanotubes in phagocytic cells. *J. Am. Chem. Soc.* 2004; 126: 15638–15639.
 184. KJ McHugh, L Jing, AM Behrens, S Jayawardena, W Tang, et al. Biocompatible Semiconductor Quantum Dots as Cancer Imaging Agents. *Adv. Mater.* 2018; 30: 1–18.
 185. AM Wagner, JM Knipe, G Orive, NA Peppas. Quantum dots in biomedical applications. *Acta Biomater.* 2019; 94: 44–63.
 186. AL Efros, DJ Nesbitt. Origin and control of blinking in quantum dots. *Nat. Nanotechnol.* 2016; 11: 661–671.
 187. Z Gao, JA Varela, L Groc, B Lounis, L Cognet. Toward the suppression of cellular toxicity from single-walled carbon nanotubes. *Biomater. Sci.* 2016; 4: 230–244.
 188. Z Yaari, Y Yang, E Apfelbaum, C Cupo, AH Settle, et al. A perception-based nanosensor platform to detect cancer biomarkers. *Sci. Adv.* 2021; 7: 852.
 189. R Nißler, AT Müller, F Dohrman, L Kurth, H Li, et al. Detektion und Visualisierung der Pflanzen-Pathogen-Response durch Nah-Infrarot-fluoreszente

- Polyphenolsensoren. *Angew. Chemie*. 2021.
190. MCY Ang, N Dhar, DT Khong, TTS Lew, M Park, et al. Nanosensor Detection of Synthetic Auxins in Planta using Corona Phase Molecular Recognition. *ACS Sensors*. 2021; 6: 3032–3046.
 191. R Langenbacher, J Budhathoki-Uprety, PV Jena, D Roxbury, J Streit, et al. Single-Chirality Near-Infrared Carbon Nanotube Sub-Cellular Imaging and FRET Probes. *Nano Lett*. 2021; 21: 6441–6448.
 192. M Card, M Gravely, SZM Madani, D Roxbury. A Spin-Coated Hydrogel Platform Enables Accurate Investigation of Immobilized Individual Single-Walled Carbon Nanotubes. *ACS Appl. Mater. Interfaces*. 2021; 13: 31986–31995.
 193. NA Bakh, X Gong, MA Lee, X Jin, VB Koman, et al. Transcutaneous Measurement of Essential Vitamins Using Near-Infrared Fluorescent Single-Walled Carbon Nanotube Sensors. *Small*. 2021; 17: 2100540.
 194. JA Stapleton, EM Hofferber, J Meier, IA Ramirez, NM Iverson. Single-Walled Carbon Nanotube Sensor Platform for the Study of Extracellular Analytes. *ACS Appl. Nano Mater*. 2021; 4: 33–42.
 195. NE Kallmyer, MS Abdennadher, S Agarwal, R Baldwin-Kordick, RL Khor, et al. Inexpensive Near-Infrared Fluorimeters: Enabling Translation of nIR-Based Assays to the Field. *Anal. Chem*. 2021; 93: 4800–4808.
 196. AJ Gillen, DJ Siefman, SJ Wu, C Bourmaud, B Lambert, et al. Templating colloidal sieves for tuning nanotube surface interactions and optical sensor responses. *J. Colloid Interface Sci*. 2020; 565: 55–62.
 197. J Pan, F Li, JH Choi. Single-walled carbon nanotubes as optical probes for bio-sensing and imaging. *J. Mater. Chem. B*. 2017; 5: 6511–6522.
 198. A Hendler-Neumark, V Wulf, G Bisker. In vivo imaging of fluorescent single-walled carbon nanotubes within *C. elegans* nematodes in the near-infrared window. *Mater. Today Bio*. 2021; 12: 100175.